

Beam Blank Mould Casting Powder**Specifications (*)**

Softening Temp (°C)	---
Flowing Temp (°C)	---
Melting Temp (°C)	1215
Bulk Density (g/cm ³)	0.84
Viscosity (at 1300 °C)(Pa.s)	1.19
Melting Speed (°C)	---
Size (0.15-1mm %)	95
H ₂ O (%)	0.30

Chemical Compositions

SiO ₂ (%)	25.7
Al ₂ O ₃ (%)	11.8
Fe ₂ O ₂ (%)	0.48
CaO (%)	30.64
MgO (%)	2.1
R ₂ O (%)	2.71
F (%)	2.19
R (%)	1.19
Csteady (%)	12.5

(*) Specifications are for reference only. We can manufacture according to customer's specifications
Spesifikasyonlar referans içindir. Müşterinin talep ettiği değerlere göre imalat yapılır.