
Synthetic Tundish Covering Powder with Calcium Aluminate

Used for all qualities except ULC, CAL and tin grades in Continuous Casting Plants to provide thermal insulation and to produce clean steel.

Chemical Analysis

MgO (%)	: 36
SiO ₂ (%)	: 6,5
Fe ₂ O ₃ (%)	: 0,5
Al ₂ O ₃ (%)	: <2
CaO (%)	: 54
Na ₂ O + K ₂ O (%)	: <0,5
C _{total} (%)	: <1

Physical Properties

Loss On Ignition at (%) (1000 °C)	: 2
Moisture (%)	: < 0,5
Grain Size (mm)	: 0 - 2
Bulk Density (kg/dm ³)	: 1

Packing

10 kg Bags